

Biobased Anethole/Polyacrylate Cross-linked Materials with Good Transparency and High Thermostability

Fengkai He, Kaikai Jin, Jing Sun and Qiang Fang**

Key Laboratory of Synthetic and Self-Assembly Chemistry for Organic Functional Molecules,
Center for Excellence in Molecular Synthesis, Shanghai Institute of Organic Chemistry,
University of Chinese Academy of Sciences, Chinese Academy of Sciences, 345 Lingling
Road, Shanghai 200032, PR China.

* E-mail: qiangfang@sioc.ac.cn.

Page 2.

¹H NMR, ¹³C NMR data and detailed test data of hardness.




Figure 1. ^1H NMR spectrum of **M2** (400 MHz, CDCl_3).




Figure 2. ^{13}C NMR spectrum of **M2** (126 MHz, CDCl_3).

Table S1. Detailed test data of hardness.

Samples	PMA	poly(MA-co-M2) _{8/1}	poly(MA-co-M2) _{4/1}	poly(MA-co-M2) _{2/1}	PM2
Hardness	54 ^[a]	114 ^[b]	117 ^[b]	121 ^[b]	123 ^[b]

[a] test data of hardness from a shore hardness tester. [b] test data of hardness from a Rockwell hardness tester.