

Supplemental Information

Characterizing the Incorporation of DNA into Single NIPAm Hydrogel Nanoparticles with Surface Plasmon Resonance Imaging Measurements

Brandon M. Matthews, Adam M. Maley, Kellen M. Kartub, and Robert M. Corn

Department of Chemistry, University of California-Irvine, Irvine, CA 92697, USA.

Table of Contents

I. Fluorescence Loss Experiments

II. Statistical Analysis of SPRI Microscopy of Complementary DNA Hybridization

I. Fluorescence Loss Measurements

Fluorescence spectra were obtained using a JASCO FP-6300 Spectrofluorometer (JASCO Analytical Instruments, Easton, MD). For SYBR Green staining experiments, parallel solutions of a 1 to 10 dilution of D1-HNPs were mixed with either 10 nM D1c or D1nc, and permitted to sit for 30 minutes. Following, SYBR Green was added to a final concentration of 0.003x, and allowed to sit for an additional 30 minutes. To remove excess unbound ssDNA or SYBR Green, Amicon Ultra – 0.5 mL Centrifugal Filter Devices 50k NMWL (MilliporeSigma, Burlington, MA) were used. Filters were pre-rinsed with buffer and centrifuged at $14,000 \times g$ for 15 minutes. 200 μL of D1-HNP mixtures were then added to the filters, and centrifuged three times at $14,000 \times g$ for 15 minutes. Each wash cycle was resuspended to 200 μL total volume, and D1-HNPs were recovered from the filters by spinning at $1,000 \times g$ for 2 minutes after the final wash. The collected mixture was brought to a total volume of 200 μL , and fluorescence measured. For fluorescence loss measurements, a standard curve was made using D1c fluorescently labeled DNA (D1c*) from 0 to 10 nM. Then, three 10 nM D1c*, 1 to 10 dilution of D1-HNPs mixtures were prepared and brought to a final volume of 1 mL. After half an hour, the mixtures were spun at 14,000 rpm for 15 minutes to create a HNP pellet at the bottom of the vial. The supernatant was removed, and measured.




Figure S1. A fluorescence curve was plotted to calculate the fluorescence of the supernatant. Approximately 35% of fluorescently labeled DNA was hybridized into D1-HNP, equal to 3.47 nM of accessible ssDNA within the HNP.

II. Statistical Analysis of SPRI Microscopy of Complementary DNA Hybridization

Table S1. SPRI Microscopy for D1c binding to D1-HNPs.

D1c concentration (nM)	$\langle \Delta \% R_{NP} \rangle$ >	standard deviation (s)	95% CI	# of NPs
0.1	5.60	1.84	0.22	276
1	5.94	2.20	0.26	282
3	6.75	2.60	0.30	414
5	7.02	3.11	0.35	304
10	6.98	2.40	0.27	307
100	7.11	2.20	0.25	314