SUPPORTING INFORMATION FOR

Packing biomolecules into Sierpiński triangles with global organizational chirality

Chao Li¹, Ruoning Li¹, Zhen Xu¹, Jie Li¹, Xue Zhang¹, Na Li¹, Yajie Zhang¹, Ziyong Shen¹, Hao Tang², Yongfeng Wang^{1,3}*

¹Key Laboratory for the Physics and Chemistry of Nanodevices and Center for Carbon-based Electronics, Department of Electronics, Peking University, Beijing 100871, China.

²CEMES-CNRS, Boîte Postale 94347, 31055 Toulouse, France

³Beijing Academy of Quantum Information Sciences, Beijing 100193, China

^{*}Correspondence to: yongfengwang@pku.edu.cn




Figure S1. Large-scale STM images of STs formed by L-Trp and BPyB molecules at low (a) and high (b) molecular coverages. STs of high orders can only be formed at low molecular coverages. Imaging conditions: (a) $V_{\text{bias}} = 0.1 \text{ V}$, I = 0.1 nA; (b) $V_{\text{bias}} = 0.2 \text{ V}$, I = 0.04 nA.




Figure S2. (a) When depositing BPyB and L-Trp molecules on Ag(111) at a ratio of BPyB to L-Try larger than 2:1, ring-like structures, clusters and one-dimension chains form on Ag(111). (**b-g**) Enlarge images of different structures and their molecular models. Scanning parameters: (a) V = 0.1 V, I = 0.04 nA; (b, d, f): V = 10 mV, I = 0.04 nA.




Figure S3. (a-c) Optimized gas-phase molecular structures of a BPyB tetramer, a L-Trp hexamer and a L-Trp-BPyB-ST-0.




Figure S4. Sierpiński triangles constructed by L-Trp and C3PC. (a) The chemical structure of C3PC and L-Trp. (**b-c**) High-resolution STM image of L-Trp-C3PC-ST-0 and its corresponding molecular model. (**d-e**) STM image of L-Trp-C3PC-ST-1 and its molecular model. Imaging conditions: (b) $V_{\text{bias}} = 10 \text{ mV}$, I = 0.04 nA; (d) $V_{\text{bias}} = 50 \text{ mV}$, I = 0.04 nA.