

Supplementary Material

Title: Dealkalization and leaching behavior of Fe, Al, Ca, Si of red mud by waste acid from titanium white production

Zhanghao Jiang^a, Xuejun Quan^{a,*}, Shuai Zhao^a, Kui Zeng^a, Hao Chen^a, Yankuo Zhou^a

^a *School of Chemistry and Chemical Engineering, Chongqing University of Technology, Chongqing 400054, China*

*Corresponding author: hengjunq@cqu.edu.cn (X. Quan).

This supplementary material includes:

Table S1. The particle size distribution table of the original and sifted RM

Table S1. The particle size distribution table of the original and sifted RM

PSD	Particle size (Raw RM)	Particle size (Sifted RM)
D03	0.230 μm	0.259 μm
D06	0.270 μm	0.325 μm
D10	0.331 μm	0.463 μm
D16	0.650 μm	0.629 μm
D25	1.149 μm	1.014 μm
D50	2.584 μm	2.397 μm
D75	3.799 μm	3.485 μm
D84	4.513 μm	4.051 μm
D90	5.658 μm	4.467 μm
D97	20.463 μm	18.803 μm