

Supporting Information

Table S1. Fragility values reported in the literature

	Fragility	Reference	Technique
PC	119	82,77	Creep
	132	73	Creep
	175	83	Dielectric
	175	96	Dielectric
	178	84	Dielectric
	165	84	DSC
	144	85	Dielectric
	170	86	DSC
PMMA	103	80	Heat capacity
	188	87	DSC
	102	88	DSC
	121	89	DSC
	115	90	Dielectric
	145	90	Creep
	93	91	Dielectric
PVC	191	73	Creep
	175	92	Activation Energies
	267	93	DSC
	160	94	Shear Modulus
PtBA	69	79	Dielectric
	62	79	Dynamic Mechanical
PnBMA	56	80	Heat capacity
	48	92	Activation Energies
	48	91	Dielectric
	48	95	DSC
PHxMA	45	80	Heat Capacity
	45	91	Dielectric