

Supplementary Information




Figure S1. Powder X-ray diffraction pattern of the Al_{30} compound after thermogravimetric analysis indicates that the final product is an amorphous aluminum (oxy)hydroxide material. This powder pattern is representative of the final product after TGA for materials containing polyaluminum cations.