

Supporting Information

TiO₂ nanorod-templated synthesis of upstanding hexagonal kassite nanosheet arrays: An intermediate route to novel nanoporous TiO₂ nanosheet arrays

Xiaoyan Gan^{a}, Xiaomin Li^a, Xiangdong Gao^a, Jijun Qiu^a, Xiudi Xiao^b*

^a State Key Laboratory of High Performance Ceramics and Superfine Microstructures, Shanghai Institute of Ceramics, Chinese Academy of Sciences, 1295 Ding Xi Road, Shanghai, 200050, P.R. China

^b Key Laboratory of Renewable Energy and Gas Hydrates, Guangzhou Institute of Energy Conversion, Chinese Academy of Sciences, Guangzhou, 510640, P.R. China

* Address correspondence to: ganxiaoyan@mail.sic.ac.cn




Figure S1. XRD pattern(a) and SEM image (b) of the sample obtained by treating the TiO_2 nanorod arrays in 10M KOH at 150°C for 5h.




Figure S2. EDS spectrum of the sample obtained by treating the TiO_2 nanorod arrays in 10M KOH at 150°C for 5h. The left insert shows the atomic percentage of the prism in the area indicated in the right insert.

