

Supporting Information:

**Self-Assembly of Nanoporous Chiral Networks with
Varying Symmetry from Sexiphenyl-dicarbonitrile on
Ag(111)**

Dirk Kühne,^{*,†} Florian Klappenberger,[†] Régis Decker,[‡] Uta Schlickum,[‡] Harald
Brune,[‡] Svetlana Klyatskaya,[¶] Mario Ruben,[¶] and Johannes V. Barth[†]

*Physik Department E20, TU München, Germany, École Polytechnique Fédérale de Lausanne,
Institut de Physique de la Matière Condensée, CH-1015 Lausanne, Switzerland, and Institute of
Nanotechnology, Forschungszentrum Karlsruhe, Karlsruhe, Germany*

E-mail: dirk.kuehne@mytum.de

Supplementary STM data

[†]Physik Department E20, TU München, Germany

[‡]École Polytechnique Fédérale de Lausanne, Institut de Physique de la Matière Condensée, CH-1015 Lausanne, Switzerland

[¶]Institute of Nanotechnology, Forschungszentrum Karlsruhe, Karlsruhe, Germany




Figure 1: STM topography ($V_B = 3.4$ V, $I_T = 0.7$ nA) for ~ 0.3 MLs of sexiphenyl-dicarbonitrile molecules on Ag(111) deposited at 110 K and cooled down to 8 K. Molecules assemble in irregular networks, in which typical binding motifs can be found. In between the networks a part of the terrace remains uncovered.