

# SUPPORTING INFORMATION

## Charge Carrier Generation and Extraction in Hybrid Polymer/Quantum Dot Solar Cells

Valentas Bertasius,<sup>1</sup> Rosanna Mastria,<sup>2,3</sup> Aurora Rizzo,<sup>2</sup> Giuseppe Gigli,<sup>2,3</sup> Carlo Giansante,<sup>2,3,4,\*</sup> Vidmantas Gulbinas<sup>1,\*</sup>


<sup>1</sup> *Center for Physical Sciences and Technology, Savanorių Ave. 231, Vilnius LT-02300, Lithuania*

<sup>2</sup> *CNR NANOTEC - Istituto di Nanotecnologia, Polo di Nanotecnologia c/o campus Ecotekne, Via Monteroni, 73100 Lecce, Italy*


<sup>3</sup> *Dipartimento di Matematica e Fisica ‘E. De Giorgi’, Università del Salento, via per Arnesano, 73100 Lecce, Italy*

<sup>4</sup> *Center for Biomolecular Nanotechnologies @UNILE, Istituto Italiano di Tecnologia, via Barsanti 1, 73010 Arnesano (LE), Italy*

\* Corresponding authors: E-mail: [carlo.giansante@unisalento.it](mailto:carlo.giansante@unisalento.it); [vidmantas.gulbinas@ftmc.lt](mailto:vidmantas.gulbinas@ftmc.lt)



**Figure S1.** TEM images of the as-casted HCs: a) HC11, b) HC21, and c) HC91.



**Figure S2.** Current-Voltage characteristics of HCx-based solar cells.

**Table S1.** Figure of merit table of HCx-based solar cells.

	$J_{SC}$ (mA/cm <sup>2</sup> )	$V_{OC}$ (V)	FF	PCE (%)
HCx11	3.24	0.62	0.41	0.82
HCx21	3.94	0.62	0.40	0.94
HCx91	11.64	0.53	0.45	2.78