

Supporting Information




Figure 1a.




Figure 1b.

Length/pixel	Length/nm
--------------	-----------

7.8100	2.52888739
5.8241	1.8858303
7.0643	2.28742361
8.5391	2.76495614
6.4026	2.07317001
10.2943	3.33328625
8.5391	2.76495614
15.5152	5.02383601
4.2426	1.37376699
10.0499	3.25414596
8.5391	2.76495647
2.8284	0.91584469
13.4114	4.34262298
11.1788	3.61970159
8.5981	2.78407734
4.9952	1.61745292
16.3931	5.30807607
9.8456	3.18802137
7.2792	2.35698922
4.1182	1.33348329
3.6055	1.16747686
12.2037	3.95155417
7.2792	2.35698939
9.2172	2.9845449
12.3547	4.00044992
7.2111	2.33495376
10.1980	3.30212276
12.2037	3.95155417
15.1238	4.89708774
11.1762	3.61885226
4.1182	1.33348346
8.2365	2.66696659
14.4222	4.66990739
4.4705	1.44754094

Average	2.88838144
Stdev	1.17700493

Table 1a.

Length/pixel	Length/nm
13.590728	2.81416409
7.2791519	1.50725759
14.849241	3.07475809
8.5390863	1.7681459
12.644423	2.61821745
19.308617	3.99813878
8.0590353	1.66874414
14.12862	2.9255427
7.0710678	1.46417065
6.3222113	1.30910868
16.154293	3.34498868
8.5981388	1.78037361
14.316264	2.96439721
11.397198	2.3599608
5.0990171	1.05582798
8.5390863	1.7681459
12.529514	2.59442382
18.10936	3.74981463
15.809237	3.27353966
11.176196	2.31419902
16.277836	3.37057011
14.12862	2.9255427
2.2352393	0.46283983
8.2364635	1.70548331
10.769529	2.22999252
8.059495	1.66883933
11.397198	2.3599608
9.4833164	1.96366291
14.422197	2.98633222
7.2110987	1.49316615
4.9952216	1.03433556
Average	2.27595629
STDEV	0.86598021

Table 1b.

Figure Captions (supporting information)

Figure 1. TEM micrographs of silver nanoparticles formed in reverse hexagonal liquid crystal. The numbers in the micrographs indicate the particles measured from two different locations of the samples, 1a) and 1b) respectively.

Table 1. The measured size of the particles marked in Figure 1a (Table 1a) and Figure 1b (Table 1b) respectively, together with the average size and standard deviation.