Supplemental Information for

Dynamic Behavior at the Interface between Lithium Cobalt Oxide and an Organic Electrolyte Monitored by Neutron Reflectivity Measurements

Taketoshi Minato,[†] Hiroyuki Kawaura,[†] Masaaki Hirayama,[§] Sou Taminato,[§] Kota Suzuki,[§] Norifumi L. Yamada,[¶] Hidetaka Sugaya,[†] Kentaro Yamamoto,[‡] Koji Nakanishi,[†] Yuki Orikasa,[‡] Hajime Tanida,[†] Ryoji Kanno,[§] Hajime Arai,[†] Yoshiharu Uchimoto[‡] and Zempachi Ogumi[†]

[†]Office of Society-Academia Collaboration for Innovation, Kyoto University, Gokasho, Uji, Kyoto 611-0011, Japan

[§] Department of Electronic Chemistry, Interdisciplinary Graduate School of Science and Engineering, Tokyo Institute of Technology, 4259 Nagatsuta, Midori-ku, Yokohama 226-8502, Japan

[¶]High Energy Accelerator Research Organization (KEK), 2-4 Shirane Shirakata, Tokai-mura, Nakagun, Ibaraki 319-1195, Japan

[‡] Graduate School of Human and Environmental Studies, Kyoto University, Sakyo-ku, Kyoto 606-8501, Japan

Table S1. Calculated values of scattering length density (SLD) of species formed by reactions of a LiCoO_2 surface and an electrolyte (1 M LiClO_4 in a vol. 1:2 solution of deuterated ethylene carbonate (EC):dimethyl carbonate (DMC)).

Species	Calculated SLD / nm ⁻²
C ₃₀ D ₆₂ O ₁₆ (PEO)	7.51×10^{-5}
C ₃₀₀ D ₆₀₂ O ₁₅₁ (PEO)	7.51×10^{-5}
$C_{3000}D_{6002}O_{1501}$ (PEO)	7.51×10^{-5}
Li ₂ CO ₃	3.48×10^{-4}
LiOD	3.88×10^{-4}
LiCl	2.26×10^{-4}
LiOCO ₂ CD ₃	4.74×10^{-4}
(LiCO ₂ CD ₂) ₂	4.45×10^{-4}