

Supporting Information

Direct Functionalization of an Acid-Terminated Nanodiamond with Azide: Enabling Access to 4-Substituted-1,2,3-Triazole Functionalized Particles

Zachary C. Kennedy, Christopher A. Barrett, and Marvin G. Warner




Figure S1: Gas (N₂) adsorption and desorption for ND-1. BET surface area: 296 m² g⁻¹.