Supporting Information

Pegylated Solanesol for Oral Delivery of Coenzyme Q₁₀

Benkai Qin, Lei Liu, Yangyang Pan, Yingchun Zhu, Xiaohe Wu, Shiyong Song^{*}, Guang Han^{*} Institute of Pharmacy, Pharmacy College of Henan University, Jinming District, Kaifeng, Henan Province 475001, China *Corresponding Author (Fax/Phone: 86-371-23880680, *Email*: pharmsong@henu.edu.cn) Alternate Corresponding Author: Guang Han (Fax/Phone: 86-371-23880680, *Email*: hang@henu.edu.cn.)

Table S1. Characterizations of CoQ₁₀-SPGS micelles.

Polymers	Size (d.nm)		PDI	CMC(µg/m	DLC(%)
SPGS-2K	103.40	±	0.200	5.36	
CoQ10-SPGS-2K	180.20	±	0.103		39.09
SPGS-5K	108.20	±	0.176	5.89	
CoQ10-SPGS-5K	186.50	±	0.134		49.00



Figure S1. X-ray diffraction patterns of CoQ₁₀ formulations: (A) CoQ₁₀ powder, (B) SPGS-5K, (C) CoQ10/SPGS-5K mixture, (D) CoQ₁₀-SPGS-2K, (E) CoQ₁₀-SPGS-5K.



Figure S2. Differential scaning calorimetry of CoQ_{10} formulations: (A) CoQ_{10} powder , (B) SPGS-5K, (C) CoQ10/SPGS-5K mixture, (D) CoQ10-SPGS-2K, (E) CoQ_{10} -SPGS-5K.



Figure S3. The particle size of CoQ_{10} -loaded SPGS micelles after storage at (A) 25 °C, (B) 4 °C.



Figure S4. Colloidal stability of diluted CoQ₁₀-loaded SPGS micelles determined by DLS.