## **Supporting Information**

Nanoscale Detection of Intermediate Solid Solutions in Equilibrated Li<sub>x</sub>FePO<sub>4</sub> Microcrystals

Brian M. May<sup>1</sup>, Young-Sang Yu<sup>1,2</sup>, Martin V. Holt<sup>3</sup>, Fiona C. Strobridge<sup>4</sup>, Ulrike Boesenberg<sup>2</sup>,

Clare P. Grey<sup>4</sup>, Jordi Cabana<sup>1,\*</sup>

## **Affiliations:**

<sup>1</sup>Department of Chemistry, University of Illinois at Chicago, Chicago, Illinois, 60607, USA <sup>2</sup>Environmental Energy Technologies Division, Lawrence Berkeley National Laboratory, Berkeley, California, 94720, USA

<sup>3</sup>Center for Nanoscale Materials, Argonne National Laboratory, Argonne, Illinois, 60441, USA

<sup>4</sup>Department of Chemistry, University of Cambridge, Lensfield Road, Cambridge CB2 1EW,

United Kingdom

\*Corresponding Author:

Jordi Cabana

jcabana@uic.edu




Figure S1. Scanning electron microscope images of the Li1(a), Li0.5 (b), and Li0 (c) particles used in this study.




Figure S2. Intensity vs. 2 plots for the summed diffraction data for each particle analyzed by SXDM. The Li1 (red) is found to contain one phase. The Li0.5 (green) displays a broad range of intensity between lithiated and an intermediate value of  $\sim$ Li<sub>0.6</sub>FePO<sub>4</sub> (low angle), with a miscibility gap between the intermediate and delithiated phases. The Li0 (blue) sample also contains intermediate phases and the delithiated phase.




Figure S3. Individual scans of the Li1 particle at different angles (a-e). Also shown is the composite image (f) from the individual scans.




Figure S4. Individual diffraction patterns representative of the phases present in the Li0.5 sample. Patterns pertaining to lithiated (close to LiFePO<sub>4</sub>) (a), intermediate (b), and delithiated (essentially, FePO<sub>4</sub>) (c) phases are shown, as well as ones that include a mixture between lithiated and intermediate (d), lithiated and delithiated (e) phases, and three different phases (f). The patterns highlight the variability in  $2\theta$  values between  $26.4^{\circ}$  and  $26.9^{\circ}$ , reflecting the broad peaks in the summed patters of Figure S2. Dashed lines denote the literature values for LiFePO<sub>4</sub> (left) and FePO<sub>4</sub> (right) in each image.




Figure S5. Individual diffraction patterns representative of the phases present in the Li0 sample. The intermediate (a) and delithiated (b) phases are shown, as well as a location containing both phases (c), and one containing multiple orientations of the delithiated phase (d). Dashed lines denote the literature value for FePO<sub>4</sub>.